1 Microplastics Identified in Commercial Over-the-counter Lubricant Eyedrops

- 2 Running Title: Microplastics Identified in Commercial Eyedrops
- 3
- 4 Authors
- 5 Julia E Jaeger, PhD¹
- 6 Matthew Burke, BSc¹
- 7 Duoduo Wu, MBBS²
- 8 Emily Ern-Min Curren, PhD³
- 9 Sandric Chee Yew Leong, PhD³
- 10 Robert Symons, PhD⁴
- 11 Blanche Xiao Hong Lim, MBBS, MMed (Ophth), FAMS^{2, 5}
- 12 Xinyi Su, MBBChir (Cantab), PhD, MMed (Ophth), FAMS^{2, 5}
- 13 Jodhbir Singh Mehta, BSc, MBBS, PhD, FRCOphth, FRCS(Ed), FAMS ^{6, 7, 8}
- 14 Andri Kartasasmita Riau, PhD^{6,7}
- 15 Chris Hong Long Lim, BSc (Med) (Hons 1), BMed, MD, PhD, MMed (Ophth), FAMS ^{2, 5, 6, 9}*
- 16

17 Affiliations

- 18 1 Eurofins Environment Testing Australia & New Zealand, Dandenong South, VIC 3175,
- 19 Australia
- 20 2 Department of Ophthalmology, National University Health System, Singapore 119228,
- 21 Singapore
- 22 3 St. John's Island National Marine Laboratory, Tropical Marine Science Institute, National
- 23 University of Singapore, Singapore 119077, Singapore
- 24 4 Eurofins Environment Testing Australia & New Zealand, Girraween, NSW 2145, Australia
- 5 Yong Loo Lin School of Medicine, National University of Singapore, Singapore 119077,
- 26 Singapore
- 27 6 Singapore Eye Research Institute, Singapore 169856, Singapore
- 28 7 Ophthalmology and Visual Sciences Academic Clinical Programme, Duke-NUS Medical
- 29 School, Singapore 169857, Singapore
- 30 8 Singapore National Eye Centre, Singapore 168751, Singapore
- 31 9 School of Optometry and Vision Science, University of New South Wales, Sydney, NSW
- 32 2052, Australia
- 33
- 34 *Author to whom correspondence should be addressed.
- 35

36 Corresponding author

- 37 Chris Hong Long Lim
- 38 chrislimmd@gmail.com
- 39 Phone number: +65 69082222
- 40
- 41 Department of Ophthalmology
- 42 1E Kent Ridge Road, NUHS Tower Block, Level 7
- 43 Singapore 119228
- 44
- 45 Financial Support: None
- 46 **Conflict of Interest:** The authors declare no conflict of interests.
- 47

48 Abstract

49 Purpose

50 There is increasing evidence that microplastics exert harmful effects on human health and

51 on the ocular surface. Recent studies have highlighted the presence of ocular surface

52 exposure to microplastics via shedding from contact lenses. This study aims to investigate if

53 microplastic particles are present in commonly used eyedrops in single-use plastic vials.

54

55 **Design**

56 Experimental study.

57

58 Methods

59 Nine commonly used commercial tear-replacement solutions available without a doctor's 60 prescription were tested (Brands A-I). All brands of evedrops were analysed visually using

61 light microscopy and the number of microplastic particles were manually counted. Brands A-

62 F were further analysed using the 8700 Agilent Laser Direct Infrared (LDIR) chemical

- 63 imaging system to identify the microplastic compositions.
- 64

65 Results

66 All eyedrops analysed contained microplastics. The number of microplastic particles

67 identified using light microscopy ranged between 15 (Brand E) to >18,000 (Brand F). In total,

68 nine types of microplastics were identified with LDIR – an average of 14 polyethylene, 8

69 polypropylene, 1 polystyrene, 2 polyvinylchloride, 21 polyethylene terephthalate, 1

polycarbonate, 19 polymethylmethacrylate, 23 polyamide and 22 polyurethane per millilitre

71 of eyedrop were identified.

72

73 Conclusions

74 This is the first study that identified microplastics in commercial tear-replacement solutions.

75 These particles may have been derived from secondary degradation of the plastic vials

76 (polyethylene) during production, transportation, or storage, and represent a major source of

exposure to the ocular surface, especially among patients who require chronic instillation of

78 eyedrops.

79 Introduction

80 Plastics are synthetic or semi-synthetic polymeric materials found commonly in everyday life.

81 Their plasticity allows them to be moulded into objects with varied shapes and rigidity,

82 making them invaluable materials in daily life and especially in healthcare ¹. Unfortunately,

83 plastics have been shown to undergo secondary degradation into smaller pieces, termed

84 microplastics and nanoplastics, when environmental factors such as mechanical abrasion,

- 85 ultraviolet irradiation and high temperatures are applied.
- 86

Microplastics are defined as plastic particles smaller than 5 mm². Primary microplastics are 87 manufactured plastic particles of small sizes, while secondary microplastics are derived from 88 89 the physical, chemical, and biological degradation of larger plastic materials found in the 90 environment. Their presence is ubiquitous in daily living, and studies have identified microplastics in air, water, food, and humans^{3,4}. As a sector heavily reliant on plastics for its 91 low cost, sterility, and plasticity, microplastics have been detected in the healthcare surgical 92 93 environment ⁵. Worryingly, microplastics were recently isolated from 49 vitreous samples of 94 patients who underwent intraocular surgery at two centres in China⁶.

95

96 There is increasing evidence that microplastics exposure may pose health risks and has 97 been implicated in the development of malignancies, endocrine and hormonal abnormalities, and abnormal foetal development ^{4,7-9}. Exposure of the ocular surface to microplastics is 98 associated with upregulation of IL-1 α , IL1- β , and IL-6 in the conjunctiva and lacrimal glands, 99 as demonstrated in murine models ¹⁰. Microplastics are also present in the atmosphere as 100 particulate matter, and population-based studies have suggested that high levels of these 101 particles may be associated with the development of dry eye disease ¹¹⁻¹³. Elevated 102 103 concentrations of microplastics in vitreous samples were also associated with higher intraocular pressures and the presence of aqueous humour opacities ⁶. Contact lenses have 104 been identified as a source of microplastics, with an estimated release of 90,000 particles on 105 106 the ocular surface from regular wear of ten hours daily over a year ¹⁴. Given the ubiguitous nature of microplastics in plastic packaging, it is conceivable that microplastics may also be 107 108 present in commercially available eyedrops. This is of particular concern as patients with 109 chronic ophthalmic conditions such as glaucoma, dry eye disease or uveitides may require 110 long-term instillation of eyedrops which exposes the ocular surface to microplastics. Thus 111 far, there is no published literature supporting the identification of microplastics in topical 112 ophthalmic formulations. This study aims to identify and characterise microplastics in 113 common over-the-counter tear-replacement solutions to ascertain whether there is a 114 potential for microplastic exposure of the ocular surface when eye drops are administered.

115

116 Methodology

117 Sample Collection

Single-use tear-replacement solutions of various brands and formulations were selected for this study. Over-the-counter commercial eyedrops with their constituent ingredients and volumes are summarised in Table 1. These formulations were chosen as they are commonly prescribed lubricants and can also be bought off-the-shelf from departmental stores and

- 122 retail pharmacies without a prescription.
- 123

124 All eyedrop samples were analysed prior to their expiry date. Two methods of analyses were

125 utilised in a microplastic-free environment – light microscopy with manual count and laser

126 direct infrared (LDIR) imaging system (Figure 1). Details of the analyses are outlined below.

127

128 Light Microscopy

Prior to analysis, all labware including forceps, glass bottles, petri dishes and metal sieves were sterilised with ethanol and rinsed with Mili-Q ultrapure water twice. In addition, glass and stainless steel labware were used to minimise external microplastic contamination. All open-lid containers were covered with either a glass slide or aluminium foil to minimise microplastic contamination from the air. All loading of eyedrop samples were conducted in a clean air cabinet. Contamination protocols undertaken during analysis are as described by Curren and Leong¹⁵.

136

137 A total of three samples of each over-the-counter tear-replacement solution were obtained. 138 Two samples were from the same production batch while a third sample was obtained from 139 another batch when possible. This allowed for comparison of microplastic counts between 140 samples of the same batch and between batches for each formulation, to determine the 141 consistency of microplastic counts between batches. Samples from tear-replacement 142 solutions were analysed by pipetting 1 mL of each eyedrop formulation using a glass pipette 143 onto a Sedgewick rafter slide and viewed under an inverted light microscope. Microplastic 144 particles were identified based on visual characteristics and sorted into categories such as 145 fibre, film, or fragment. The number of microplastics in each sample was determined from 146 triplicate counts. A blank controls were used prior to each evedrop samples count analysis to

- 147 ensure that no ambient microplastic contamination was present prior to testing.
- 148

149 Laser Direct Infrared Imaging System with Spectroscopy

LDIR is an infrared spectrometer that utilises a fast-tuneable quantum-cascade laser (QCL) coupled with a rapidly scanning imaging system to analyse particulate information such as quantification, size, colour and morphology, while identification of polymer type can be identified with spectroscopic analysis ¹⁶.

154

155 To prevent environmental contamination, the LDIR analysis was performed in a segregated 156 room within the facility, physically distinct and equipped with an airlock system and change 157 pod. The laboratory was kept at a positive pressure and air inflow HEPA filtered. Lab 158 analysts also don specialised black cotton lab coats with efforts made to avoid clothing that 159 is prone to shedding polymer fibres. All glassware underwent either furnace cleaning for a 160 minimum of 4 hours at temperatures exceeding 400 °C or washing with microplastics-161 analysis-grade (MAG) water. Prior to use, MAG water samples were analysed to ascertain 162 their purity. Sample filtration was performed within a fume cupboard, with samples left in the 163 cupboard for over 5 minutes covered with foil. Monthly air blank tests are conducted to 164 assess the air quality within the laboratory and the fume cupboard. Nightly vacuuming and 165 regular surface wiping are also conducted to remove potential contaminants. Quality control 166 and accuracy of analysis was assessed by running samples with a known concentration of 167 green polyethylene (PE) and analysing reagent blanks using 1 L of MAG water. A polymer 168 register is also diligently updated to track and trace potential contaminations. 169

Reference materials for the analysis were obtained from various manufacturers: fluorescent
green PE microspheres of 75-90 µm and 250-300 µm (Cospheric, Santa Barbara, CA, USA),
polypropylene (PP) chromatographic grade of 150 µm (Polysciences Inc, Warrington, PA,
USA), polystyrene (PS) EZY-CALTM microsphere size standard, NIST-traceable with mean
diameter 30 or 70 µm, and a concentration of 2,000 particles/mL (ThermoFisher Scientific

175 Waltham, MA, USA), polyvinylchloride (PVC) analytical standard (Sigma-Aldrich, Saint 176 Louis, MO, USA), polyethylene terephthalate (PET) with a maximum particle size of 300 µm 177 (Goodfellow, Cambridge, United Kingdom), polycarbonate (PC) beads sized 150-250 µm 178 (Sigma- Aldrich, Saint Louis, MO, USA), polymethylmethacrylate (PMMA) analytical 179 standard with a size of 50 µm in solution (Sigma-Aldrich, Saint Louis, MO, USA), polyamide 180 (PA6, Nylon) with a mean size of 15-20 µm (Goodfellow, Cambridge, United Kingdom), 181 polyurethane (PU) 3-5 mm (Goodfellow, Cambridge, United Kingdom), and POLYMER KIT 182 1.0 (Hawaii Pacific University, Honolulu, HI, USA). MAG water was obtained by filtering 183 ultrapure water from Arium® Mini water purification system connected to a CellPlus Ultrafilter 184 (Sartorius, Göttingen, Germany) and three subsequent filtrations through a 5 µm 185 polycarbonate filter.

186

187 To analyse microplastic content in commercially available tear-replacement solutions, two different kinds of analysis were used: MirrIR low-e microscope slides (Kevley Technologies, 188 189 Chesterland, OH, USA) analysis (slide) and on-filter analysis (filter). A separate production 190 batch of tear-replacement solutions was obtained for this analysis. For every brand of 191 eyedrop, two replicates of on-slide analysis and one on-filter analysis were conducted. For 192 slide analysis, the entire content (0.4 mL) of a tear-replacement vial was filtered through a 5 193 um pore size polycarbonate filter paper (Sartorius, Göttingen, Germany) mounted in a glass 194 vacuum filtration unit with a funnel (Rocker, Kaohsiung, Taiwan) attached to a vacuum pump 195 (Wiggens, Wuppertal, Germany). The filter was then rinsed with 100 mL of MAG water. All 196 particles were transferred onto a slide for analysis. On-filter analysis of the gold filter was 197 also performed to avoid the potential loss due to the transfer. Filtration was performed with 198 25 mm diameter, 0.8 µm pore size gold-coated polycarbonate membrane filters (Sterlitech, 199 Aubrun, WA, USA). The entire content (0.4 mL) of one eyedrop vial was administered 200 through the filter directly and washed with 100 mL of MAG water. Once dry, the filter was 201 mounted on a filter holder (Agilent Technologies, Santa Clara, CA, USA) and analysed. For 202 the analysis of the tear-replacement vial compositions, small fragments < 300 µm of the vial 203 have been cut off and placed onto a slide for analysis.

204

205 All samples were analysed to quantify polymer particles and size ranges between 20 and 206 500 µm on the Agilent 8700 LDIR chemical imaging system (Agilent Technologies, Santa 207 Clara, CA, USA). Particles larger than 500 µm were not detected. The analyses were 208 conducted by the automated Particle Analysis workflow as part of the Clarity software 209 Version 1.5 (Agilent Technologies, Santa Clara, CA, USA). This workflow automatically 210 counts and sizes all particles. High-magnification images can also be taken during the 211 analysis. For particle identification, an IR spectrum is generated in the fingerprint region 212 $(1800 - 975 \text{ cm}^{-1})$. The acquired spectra was then compared to an internal library. The 213 library used in this study is based on siMPle, which has been modified for the use of the LDIR chemical imaging system ¹⁷. Additionally, information from open-source repositories 214 215 such as µATR-FTIR Spectral Libraries of Plastic Particles (FLOPP and FLOPP-e) for the Analysis of Microplastics have been intergraded ^{17,18}. Finally, the library was also modified by 216 217 Eurofins Environment Testing for the nine reported polymers which were verified against two 218 independently purchased reference materials. 219

220 The match quality was determined by comparing the acquired spectra to the library

221 reference spectra. A higher quality match score indicates a better fit between the measured

spectrum and the material's spectrum, with a score of 1 representing an absolute match. Forthis study, a minimum match quality above 0.7 was deemed necessary.

224

225 Results

226 The number of visually identified microplastic particles in each 1 mL sample via light

- 227 microscopy is summarised with a logarithmic scale in Figure 2. Eyedrops from a separate
- production batch were not available for brands C, D, F and I, hence light microscopy
- analysis was performed only for two samples from within the same production batch.
- 230 Notably, Brand F had a cloudy appearance during analysis, and yielded the largest number
- 231 of possible microplastic particles (>18,000 per millilitre of eyedrop) among all the tear-
- replacement samples tested. Even among eyedrops from the same production batch, the
- 233 number of microplastic particles remained varied.
- 234
- LDIR analysis was performed for seven tear-replacement brands (Brands A-F). Two
- 236 replicates of on-slide analysis and one on-filter analysis were performed for all samples. All
- 237 samples showed evidence of microplastic contamination (Table 2) (Figure 3). Nine types of
- 238 microplastics were identified polyamide (PA), polycarbonate (PC), polyethylene (PE),
- 239 polyethylene terephthalate (PET), polymethylmethacrylate (PMMA), polypropylene (PP),
- 240 polystyrene (PS), polyurethane (PU), and polyvinylchloride (PVC) (Figure 4). These
- 241 microplastics were identified in varying levels in each tear-replacement sample and ranged
- between 20-500 μm. The amount and type of microplastic particles retrieved from each unit
- dose vial varied. This ranged between five and 308 particles per 1 mL of eyedrop (Table 2).
- The most identified microplastic types were PET, PA and PU, which were identified in 16, 15 and 14 samples respectively. Analysis of tear-replacement solution vials shows that they are
- 246 made of PE.
- 247

248 Discussion

249 This study is the first to identify the presence of microplastics in tear-replacement solutions 250 in single-use vials, adding to a growing body of evidence on the pervasive nature of 251 microplastics⁴. Over-the-counter topical tear-replacement solutions were analysed in this 252 pilot study as these were commonly available across international markets and readily accessible without a prescription ¹⁹. Patients with ocular surface disorders are frequently 253 254 prescribed topical tear-replacement agents and preservative-free formulations, which are 255 thought to be innocuous, with increased frequency of administration considered useful and 256 often encouraged to supplement either an unhealthy and unstable tear film or improve a 257 poor ocular surface. Frequent use of these topical formulations may therefore inadvertently 258 expose the ocular surface to significant levels of microplastics.

259

260 Microplastic particles were identified in all evedrop samples, with PET, PA and PU being the 261 most commonly identified. This is a concerning observation as microplastics have been associated with multiple adverse health impacts ⁷⁻⁹, and may adversely impact patients who 262 263 rely on regular instillation of eyedrops for ophthalmic diseases. A compromised ocular 264 surface such as in severe dry eye disease, Steven Johnson Syndrome and ocular mucous 265 membrane pemphigoid may also be more susceptible to the negative impacts of 266 microplastics. Owing to its small size, microplastics have a high surface-area-to-volume ratio and bioaccessibility and can exert harmful effects at a cellular level ²⁰. These are postulated 267 268 to occur via three main mechanisms - inflammation and oxidative damage, microbial 269 dysbiosis and toxicological effects from additives and sequestrated chemicals ¹⁶.

270

271 In-vitro studies with human cornea and conjunctival epithelial cell lines have demonstrated 272 the uptake of polystyrene particles with subsequent accumulation around the cell nuclei 273 when they were administered topically ¹⁰. Cytotoxicity of the PS particles resulted in 274 decreased cell viability and was associated with a reduction in proliferation markers. 275 Exposure of the ocular surface of murine models to 50 nm or 2 µm polystyrene microplastics 276 thrice daily for two to four weeks further demonstrated a clinical reduction in tear secretion, compared to both mice receiving normal saline or controls which received no eyedrops ¹⁰. 277 278 Further ex-vivo analysis of tissues revealed reduced size and density of conjunctival goblet 279 cells with an irregular arrangement of lacrimal gland acini in mice treated with microplastics. 280 Congruent to findings in human cornea and conjunctival epithelial cell lines, proliferation-281 related markers such as Ki-67, p63, and K14 were downregulated, while inflammatory 282 cytokines including IL-1 α , IL1- β , and IL-6 were upregulated in murine models exposed with their ocular surface exposed to polystyrene microplastics in a time-dependent fashion ¹⁰. 283 284

285 Microplastics and their degradation products may also harbour toxic chemicals arising from 286 additives during production, or chemicals absorbed from the environment. A contaminant of 287 concern harboured by plastics are per- and polyfluoroalkyl substances (PFAS) which have 288 been shown to induce immune, cardiovascular, endocrine, and hepatic dysfunction and increase the risk of developing malignancies ^{21,22}. Contact lenses have been shown to be a 289 290 source of microplastic exposure, and a recent study showed that contact lens usage was associated with elevated serum PFAS levels among young adults ^{14,23}. While tear 291 292 homeostasis and the blink mechanism help with regulating tear volume, their role in clearing 293 microplastics and contaminants of emerging concern remains unexplored ²⁴. This represents 294 an urgent need to characterise and identify potential ocular exposure of microplastics among 295 ophthalmic therapeutics to prevent long-term adverse effects.

296

297 This study employed two different methods to determine the presence of microplastics in 298 commercially available tear-replacement solutions. A range of techniques have been described in the literature to analyse microplastics ¹⁶. These include non-destructive 299 300 methods such as transmission electron microscopy, scanning electron microscopy, atomic 301 force microscopy, Raman spectroscopy, atomic force microscopy, and destructive methods 302 such as thermal analysis using pyrolysis or thermal desorption gas chromatography-mass 303 spectrometry (Pyr/TD-GC-MS), and other thermogravimetric analysis (TGA)-based method ¹⁶. There is no consensus on a standardised approach to processing and analysing samples 304 305 for microplastics. Variations in counts obtained reflect the differences in technique and 306 limitations of each of the approaches taken. For instance, with sample F, although more than 307 8000 possible microplastic particles were identified in 1 mL of the sample using light 308 microscopy visualisation, only 48 to 141 particles were definitively identified as microplastics 309 using triplicate analysis with LDIR. This may be related to the constituents of the sample, 310 which contains castor oil and carbomer copolymer type A particles.

311

This highlights the limitations of visual identification with light microscopy in microplasticsanalysis. The variation of microplastic counts during visual identification with light

314 microscopy ranges between 20-70 % and increases with smaller particle sizes ^{25,26}. Factors

315 that affect identification rates include the operator's experience, the complexity of the sample

316 matrix, microplastic particle size and the quality and magnification of the microscope ^{16,25,27}.

Therefore, it is recommended that additional analytical methods be performed in conjunction with light microscopy to reduce error rates and overcome its limitations ¹⁶.

319

320 The LDIR can reliably measure particle sizes from 20 µm in size, and further identify the 321 composition of each individual particle through spectroscopic comparison against 322 established spectral libraries. In the current study, the number of microplastics varied even 323 among the same brands of tear-replacement solutions (Figure 3). This may be related to 324 analytical methodology and environmental confounders which could not be controlled. The 325 Agilent LDIR imaging system possesses the ability to automate the analysis of samples for 326 microplastics. Underestimation may ensue when particles in the sample agglomerate or 327 stack on top of each other, that requires an operator to manually analyse inaccurate components ²⁸. The identification capability of LDIR is dependent on the robustness and 328 329 extensiveness of the spectral library used. Environmental factors such as physical stress, 330 heat, chemical additives, and contamination may alter the morphology and chemical 331 composition of microplastics. These factors are influenced by manufacturing, transport, and 332 storage conditions of the tear-replacement solutions before procurement in this study. 333 Although samples from two production batches were acquired when possible, it is difficult to 334 control and assess the extent of degradation of plastic vials prior to analysis. Moreover, 335 analysis was performed in this study by referencing both a proprietary and in-house spectral 336 database. These databases are not exhaustive and further work remains useful to 337 characterise the spectral characteristics of microplastics to improve the accuracy of current spectroscopic methods ²⁹⁻³¹. In this study, a spectral match quality of 70% between the 338 339 sample particle and database was considered to be strong evidence that the particle is of the 340 same polymer type as the reference. Currently, no universally accepted guidelines exist, but 341 previous studies have suggested 70-80% match guality as the cut-off for polymer-type identification ^{32,33}. The California State Water Resources Control Board defines 70% or 342 above as the threshold for an accurate spectral match ³⁴. Further studies investigating the 343 344 impact of temperature, physical stress, ultraviolet light, and other environmental factors 345 experienced during the production, transport and storage of tear-replacement solution vials 346 are required to ascertain whether the majority of microplastics arise from manufacturing 347 processes, or from post-production conditions.

348

349 Smaller microplastics particles have the propensity to exert more deleterious effects on cells. 350 This is postulated to be related to increased bioaccessibility and altered surface chemistry ³⁵. 351 Smaller nanoplastic particles have been reported to cause greater intestinal mucosal 352 damage, while larger nanoplastic particles induce greater microbial dysbiosis in tilapias 353 (Oreochromis niloticus)³⁶. In a human intestinal in-vitro model (Caco-2 cell line), smaller 100 354 nm polystyrene microplastic particles were associated with increased intestinal toxicity 355 compared to 5 µm particles ³⁷. As LDIR can reliably identify particles from 20 µm, smaller 356 particles including nanoplastics (<1 nm) were not analysed in the current study. Further 357 characterisation of these particulate properties with techniques such as pyrolysis or thermal 358 desorption gas chromatography-mass spectrometry conferring higher resolution compared 359 to LDIR will be beneficial in future studies.

360

The impact of microplastics on human health represents an evolving and developing field. Although microplastics were identified from all tested samples, safe levels of exposure and

363 the potential physiological and toxicological effects of microplastics have yet to be

364 determined. This is compounded by the extensive range of chemicals and additives used in

the manufacture of different types of plastics. Cradle-to-consumer conditions, including
environmental conditions during storage and transport, may influence the stability of plastics
housing these drops and contribute to the leeching of chemicals or additives into the topical
tear replacement formulations. Future work to quantify microplastics in a range of topical
ophthalmic formulations and develop an understanding of inherent risk factors contributing to
the instability of the microplastics should be considered. Effects of microplastics retention

- the instability of the microplastics should be considered. Effects of microplastics retention from chronic instillation over the ocular surface can also be investigated via animal and
- from chronic instillation over the ocular surface can also be investigated via animal and
- 372 human studies.
- 373

374 Conclusion

375 This study demonstrated the presence of microplastics in commonly used tear-replacement

- 376 solutions. The discovery of microplastics in therapeutics used on the ocular surface,
- 377 including contact lenses and eyedrops, raises significant concerns regarding their impact on
- 378 the ocular surface. Therefore, it is crucial to direct our attention towards identifying,
- 379 characterising, and addressing potential microplastics throughout the lifecycle of these
- 380 products. Only by doing so can we take proactive steps to minimise ocular surface exposure
- to microplastics and reduce potential damage to the ocular surface, especially among
- 382 patients who rely chronically on these therapeutic agents.
- 383

384 Acknowledgements

385 The study was partly funded by the SERI-Lee Foundation Grant (R1845/87/2021). We thank 386 Eurofins Scientific for supporting this study with experimentation and microplastics analysis

Eurofins Scientific for supporting this study with experimentation and microplastics analysis
 with laser direct infrared imaging system with spectroscopy. Illustration was created with

388 BioRender.com.

390 Figures and Tables

391

392 Table 1: Composition of selected tear-replacement solutions.

Brand	Ingredients	Volume		
A	Carmellose sodium* Sodium chloride Sodium lactate Potassium chloride Calcium chloride dihydrate Magnesium chloride hexahydrate Purified water Sodium hydroxide Hydrochloric acid	0.4 ml		
В	Carboxymethylcellulose sodium* Sodium lactate Sodium lactate Potassium chloride Calcium chloride dihydrate Magnesium chloride hexahydrate Purified water Sodium hydroxide Hydrochloric acid	0.4 ml		
с	Carboxymethylcellulose sodium* Glycerin* Boric acid Calcium chloride dihydrate Erythritol Levocarnitine Magnesium chloride hexahydrate Potassium chloride hexahydrate Potassium chloride potentiate Stabilized oxychloro complex Sodium borate decahydrate Sodium citrate dihydrate	0.4 ml		
D	Polyvinyl Alcohol* Povidone* Sodium chloride Purified water Sodium hydroxide Hydrochloric acid	0.4 ml		
E	Dextran* Hypromellose* Potassium chloride Purified water Sodium borate Sodium chloride Sodium hydroxide Hydrochloric acid	0.8 ml		
F	Carboxymethylcellulose sodium* Glycerin* Polysorbate* Boric acid Carbomer copolymer type A Castor oil Erythritol Levocarnitine Punfied water Sodium hydroxide Hydrochloric acid	0.4 ml		
G	Polyethylene glycol* Propylene glycol* Hydroxypropyl guar Sorbitol Aminomethyl Propanol Boric acid Potassium chloride Sodium chloride	0.7 ml		
н	Polyethylene glycol 400* Sodium hyaluronate Boric Acid Sodium borate (Calcium chloride (dihydrate) Magnesium Chloride Sodium chloride Potassium chloride	0.4 ml		

I	Sodium carboxymethylcellulose* Sodium hyaluronate* Glycerin	0.4 ml	
	Erythrol		
	Levocarnitine		
	Sodium lactate Calcium chloride dibydrate		
	Magnesium chloride hexahydrate		
	Potassium chloride		

393 394

395 Table 2: Number and type of microplastics per millilitre identified via laser direct 396 information provides and type of microplastics per millilitre identified via laser direct

396 infrared imaging system with spectroscopy.

397

Sample	Polyethyle ne (PE)	Polypropy lene (PP)	Polystyre ne (PS)	Polyvinylc hloride (PVC)	Polyethyle ne Terephtha late (PET)	Polycarbo nate (PC)	Polymeth ylmethacr ylate (PMMA)	Polyamide (PA)	Polyureth ane (PU)	Total
A-Slide 1	43	15	3	0	8	0	75	78	88	308
A-Slide 2	1	1	0	0	3	3	0	0	0	8
A-Filter	15	0	0	6	75	0	0	5	8	108
B-Slide 1	3	8	0	3	3	0	38	179	45	276
B-Slide 2	3	28	0	0	3	0	13	30	13	88
B-Filter	28	3	0	0	106	0	0	15	53	203
C-Slide 1	41	41	3	8	28	6	93	0	26	241
C-Slide 2	0	0	0	3	3	0	0	0	0	5
C-Filter	5	0	0	5	31	0	5	8	18	71
D-Slide 1	0	3	0	0	0	0	0	5	0	8
D-Slide 2	0	0	0	0	5	3	0	45	3	55
D-Filter	5	0	3	0	21	0	0	3	10	41
E-Slide 1	0	6	0	0	4	0	53	10	43	115
E-Slide 2	1	0	0	0	10	0	0	14	1	26
E-Filter	59	1	0	3	7	0	3	10	23	106
F-Slide 1	0	5	3	0	0	0	48	3	36	93
F-Slide 2	0	18	0	0	3	0	15	0	13	48
F-Filter	46	8	0	0	60	3	0	3	23	141

Figure 1: Summary experimental workflow of analysis with light microscopy and laser
 direct infrared imaging system with spectroscopy.



401

402 *Samples were obtained from a second production batch whenever possible.

403

Figure 2: Number of visually identified microplastic particles using light microscopy.
 Samples were obtained from across two production batches from each tear-

- 406 replacement brand when possible.
- 407



410 Figure 3: Number and type of microplastic particles identified using laser direct

411 infrared imaging system with spectroscopy. Two different kinds of analyses were

412 used: Kevley slide analysis (slide) and on-filter analysis (filter).

413



- 417 Figure 4: Representative images of (A) polyamide, (B) polyethylene terephthalate, (C)
- 418 polyethylene, (D) polystyrene, (E) polycarbonate, and (F) polypropylene identified in
- 419 tear-replacement solutions using laser direct infrared imaging system with
- 420 spectroscopy. Blue dotted lines represent reference spectra and red solid lines

421 represent measured spectra.



423 References 424 Jain N, LaBeaud D. How Should US Health Care Lead Global Change in Plastic 1. 425 Waste Disposal? AMA J Ethics. Oct 1 2022;24(10):E986-993. 426 doi:10.1001/amajethics.2022.986 427 Dris R, Agarwal S, Laforsch C. Plastics: From a Success Story to an Environmental 2. 428 Problem and a Global Challenge. *Glob Chall.* Jun 2020;4(6):2000026. 429 doi:10.1002/gch2.202000026 430 Leslie HA, van Velzen MJM, Brandsma SH, Vethaak AD, Garcia-Vallejo JJ, Lamoree 3. 431 MH. Discovery and quantification of plastic particle pollution in human blood. Environ Int. 432 May 2022;163:107199. doi:10.1016/j.envint.2022.107199 433 4. Microplastics are everywhere - we need to understand how they affect human health. 434 Nat Med. Apr 2024;30(4):913. doi:10.1038/s41591-024-02968-x 435 5. Field DT, Green JL, Bennett R, et al. Microplastics in the surgical environment. 436 Environ Int. Dec 2022;170:107630. doi:10.1016/j.envint.2022.107630 437 6. Zhong Y, Yang Y, Zhang L, et al. Revealing new insights: Two-center evidence of 438 microplastics in human vitreous humor and their implications for ocular health. Sci Total 439 Environ. Apr 15 2024;921:171109. doi:10.1016/j.scitotenv.2024.171109 440 Pauly JL, Stegmeier SJ, Allaart HA, et al. Inhaled cellulosic and plastic fibers found in 7. 441 human lung tissue. Cancer Epidemiol Biomarkers Prev. May 1998;7(5):419-28. 442 Ragusa A, Svelato A, Santacroce C, et al. Plasticenta: First evidence of microplastics 8. 443 in human placenta. Environ Int. Jan 2021;146:106274. doi:10.1016/j.envint.2020.106274 444 9. Jin H, Yan M, Pan C, et al. Chronic exposure to polystyrene microplastics induced 445 male reproductive toxicity and decreased testosterone levels via the LH-mediated 446 LHR/cAMP/PKA/StAR pathway. Part Fibre Toxicol. Feb 17 2022;19(1):13. 447 doi:10.1186/s12989-022-00453-2 448 Zhou X, Wang G, An X, et al. Polystyrene microplastic particles: In vivo and in vitro 10. 449 ocular surface toxicity assessment. Environ Pollut. Jun 15 2022;303:119126. 450 doi:10.1016/j.envpol.2022.119126 451 Hao R, Zhang M, Zhao L, et al. Impact of Air Pollution on the Ocular Surface and 11. 452 Tear Cytokine Levels: A Multicenter Prospective Cohort Study. Front Med (Lausanne). 453 2022:9:909330. doi:10.3389/fmed.2022.909330 454 Mu J, Zeng D, Fan J, et al. Associations Between Air Pollution Exposure and Daily 12. 455 Pediatric Outpatient Visits for Dry Eye Disease: A Time-Series Study in Shenzhen, China. Int 456 J Public Health. 2021;66:1604235. doi:10.3389/ijph.2021.1604235 457 Kim Y, Choi YH, Kim MK, Paik HJ, Kim DH. Different adverse effects of air pollutants 13. 458 on dry eye disease: Ozone, PM(2.5), and PM(10). Environ Pollut. Oct 2020;265(Pt 459 B):115039. doi:10.1016/j.envpol.2020.115039 460 14. Liu Y, Ling X, Jiang R, et al. High-Content Screening Discovers Microplastics 461 Released by Contact Lenses under Sunlight. Environ Sci Technol. Jun 13 2023;57(23):8506-462 8513. doi:10.1021/acs.est.3c01601 463 Curren E, Leong SCY. Profiles of bacterial assemblages from microplastics of 15. 464 tropical coastal environments. Sci Total Environ. Mar 10 2019;655:313-320. 465 doi:10.1016/i.scitotenv.2018.11.250 466 Wu D, Lim BXH, Seah I, et al. Impact of Microplastics on the Ocular Surface. Int J 16. 467 Mol Sci. Feb 15 2023;24(4)doi:10.3390/ijms24043928 468 Primpke S, Cross RK, Mintenig SM, et al. Toward the Systematic Identification of 17. 469 Microplastics in the Environment: Evaluation of a New Independent Software Tool (siMPle) 470 for Spectroscopic Analysis. Appl Spectrosc. Sep 2020;74(9):1127-1138. 471 doi:10.1177/0003702820917760 472 18. De Frond H, Rubinovitz R, Rochman CM. µATR-FTIR Spectral Libraries of Plastic 473 Particles (FLOPP and FLOPP-e) for the Analysis of Microplastics. Anal Chem. Dec 7 474 2021;93(48):15878-15885. doi:10.1021/acs.analchem.1c02549 475 Pucker AD, Ng SM, Nichols JJ. Over the counter (OTC) artificial tear drops for dry 19. 476 eye syndrome. Cochrane Database Syst Rev. Feb 23 2016;2(2):Cd009729. 477 doi:10.1002/14651858.CD009729.pub2

20. 478 Chen G, Feng Q, Wang J. Mini-review of microplastics in the atmosphere and their 479 risks to humans. Sci Total Environ. Feb 10 2020;703:135504. 480 doi:10.1016/j.scitotenv.2019.135504 481 Jane LEL, Yamada M, Ford J, Owens G, Prow T, Juhasz A. Health-related toxicity of 21. emerging per- and polyfluoroalkyl substances: Comparison to legacy PFOS and PFOA. 482 483 Environ Res. Sep 2022;212(Pt C):113431. doi:10.1016/j.envres.2022.113431 484 Wen ZJ, Wei YJ, Zhang YF, Zhang YF. A review of cardiovascular effects and 22. 485 underlying mechanisms of legacy and emerging per- and polyfluoroalkyl substances (PFAS). 486 Arch Toxicol. May 2023;97(5):1195-1245. doi:10.1007/s00204-023-03477-5 487 Kang H, Kim DH, Choi YH. Elevated levels of serum per- and poly-fluoroalkyl 23. 488 substances (PFAS) in contact lens users of U.S. young adults. Chemosphere. Feb. 489 2024;350:141134. doi:10.1016/j.chemosphere.2024.141134 490 24. Palakuru JR, Wang J, Aquavella JV. Effect of blinking on tear volume after instillation 491 of midviscosity artificial tears. Am J Ophthalmol. Dec 2008;146(6):920-4. 492 doi:10.1016/j.ajo.2008.06.020 493 Hidalgo-Ruz V, Gutow L, Thompson RC, Thiel M. Microplastics in the marine 25. 494 environment: a review of the methods used for identification and quantification. Environ Sci 495 Technol. Mar 20 2012;46(6):3060-75. doi:10.1021/es2031505 496 Eriksen M, Mason S, Wilson S, et al. Microplastic pollution in the surface waters of 26. 497 the Laurentian Great Lakes. Mar Pollut Bull. Dec 15 2013;77(1-2):177-82. 498 doi:10.1016/j.marpolbul.2013.10.007 499 Mariano S, Tacconi S, Fidaleo M, Rossi M, Dini L. Micro and Nanoplastics 27. 500 Identification: Classic Methods and Innovative Detection Techniques. Front Toxicol. 501 2021;3:636640. doi:10.3389/ftox.2021.636640 502 28. Tian X, Beén F, Bäuerlein PS. Quantum cascade laser imaging (LDIR) and machine 503 learning for the identification of environmentally exposed microplastics and polymers. 504 Environ Res. Sep 2022;212(Pt D):113569. doi:10.1016/j.envres.2022.113569 505 Araujo CF, Nolasco MM, Ribeiro AMP, Ribeiro-Claro PJA. Identification of 29. 506 microplastics using Raman spectroscopy: Latest developments and future prospects. Water 507 Res. Oct 1 2018;142:426-440. doi:10.1016/j.watres.2018.05.060 508 30. Palmer A, Phapale P, Fay D, Alexandrov T. Curatr: a web application for creating, 509 curating and sharing a mass spectral library. *Bioinformatics*. Apr 15 2018;34(8):1436-1438. 510 doi:10.1093/bioinformatics/btx786 511 Cowger W, Steinmetz Z, Gray A, et al. Microplastic Spectral Classification Needs an 31. 512 Open Source Community: Open Specy to the Rescue! Anal Chem. Jun 1 2021;93(21):7543-513 7548. doi:10.1021/acs.analchem.1c00123 514 Ghanadi M, Joshi I, Dharmasiri N, et al. Quantification and characterization of 32. 515 microplastics in coastal environments: Insights from laser direct infrared imaging. Sci Total 516 Environ. Feb 20 2024;912:168835. doi:10.1016/j.scitotenv.2023.168835 517 Morgado V, Palma C, Bettencourt da Silva RJN. Microplastics identification by 33. 518 infrared spectroscopy - Evaluation of identification criteria and uncertainty by the Bootstrap 519 method. Talanta. Mar 1 2021;224:121814. doi:10.1016/j.talanta.2020.121814 520 Standard Operating Procedures for Extraction and Measurement by Infrared 34. 521 Spectroscopy of Microplastic Particles in Drinking Water (2021). 522 Mahmoudi M, Lynch I, Ejtehadi MR, Monopoli MP, Bombelli FB, Laurent S. Protein-35. 523 nanoparticle interactions: opportunities and challenges. Chem Rev. Sep 14 524 2011;111(9):5610-37. doi:10.1021/cr100440g 525 36. Hao T, Gao Y, Li ZC, Zhou XX, Yan B. Size-Dependent Uptake and Depuration of 526 Nanoplastics in Tilapia (Oreochromis niloticus) and Distinct Intestinal Impacts. Environ Sci 527 Technol. Feb 21 2023;57(7):2804-2812. doi:10.1021/acs.est.2c08059 528 Liu S, Wu X, Gu W, Yu J, Wu B. Influence of the digestive process on intestinal 37. 529 toxicity of polystyrene microplastics as determined by in vitro Caco-2 models. Chemosphere. 530 Oct 2020;256:127204. doi:10.1016/j.chemosphere.2020.127204







6	0.2 0.1 1800 1600 1400 1200 1000 Werenumber (cm ³)
Polyamide (PA) P (2 Quality, 0.833 Bid A 344 E Accept Prediction Width 20.00 µm Diameter 24.59 µm Heleyth 30.00 µm Area 475.00 µm ² Heley Duable Clock to add motory	

1800 1600



D

0.4

1400 1200 1000

Wavenumber (cm⁻¹)



Е

Polvethylene (PE)

Width 204.00 µm

Height 255.00 µm

Notes Double click to odd notes

Accept Prediction

Diameter 179.83 µm Area 25400.00 µm³

Quality 0.956

Id# A24

A

С

Le				1500 1600 1400 1200 1000 Wearnamber (m [*])
Polyca	arbonate (I	PC)	70	
ld #		Accept	Prediction	1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1
Width		Diameter		the state of the s
Height				
Notes				



	1800 1000 1400 1200 1000 Warenuther (m ²)
Polypropylene (PP) ↗ ₪ Quality 0.944 8 # A225 ☑ Accept Prediction Width 43.00 µm Diameter 37.64 µm	
Height 37.00 µm Area 1112.50 µm ²	