

**Table S2A: Integrity Results for Face Masks (MMs and CM)**

Integrity Test	Decontamination method	WHO Type II mask (FW)			Halyard type IIR mask (FH)			Community mask (CM)		
		N	Mean (SD)	p-value*	N	Mean (SD)	p-value*	N	Mean (SD)	p-value*
NaCl Filtration Efficiency (%) ( <i>Standard: ≥95% for respirators</i> )	Untreated	5	76.32 (1.54)	ref	5	85.78 (1.71)	ref	5	33.92 (13.66)	ref
	MBL 5x	5	85.30 (0.89)	0.012	5	93.58 (0.68)	0.012	5	32.42 (1.91)	0.14
	DH 5x	5	80.70 (4.79)	0.21	5	86.94 (0.66)	0.35	5	46.94 (12.65)	0.09
	VHP+O <sub>3</sub> 5x	5	85.80 (1.48)	0.012	5	93.13 (0.48)	0.012	N/A	N/A	N/A
Bacterial Filtration Efficiency (%) ( <i>Standard: ≥98% for EN 14683 and 98≥% ASTM F2100</i> )	Untreated	10	99.38 (0.20)	ref	10	99.72 (0.16)	ref	10	87.59 (4.06)	ref
	MBL 5x	10	99.40 (0.26)	0.85	10	99.74 (0.14)	0.88	10	90.88 (2.40)	0.04
	DH 5x	10	99.23 (0.14)	0.07	10	99.81 (0.10)	0.18	10	86.59 (2.21)	0.50
	VHP+O <sub>3</sub> 5x	5	99.20 (0.16)	0.10	5	99.64 (0.13)	0.31	N/A	N/A	N/A
Breathing Resistance with NaCl Inhalation mmH <sub>2</sub> O ( <i>Standard: ≤35 mmH<sub>2</sub>O for respirators</i> )	Untreated	3	9.37 (0.74)	ref	3	11.87 (2.05)	ref	3	8.10 (1.42)	ref
	MBL 5x	3	8.97 (0.81)	0.56	3	9.50 (1.73)	0.20	3	4.20 (0.00)	0.04
	DH 5x	3	8.93 (0.90)	0.55	3	8.43 (1.91)	0.10	3	3.43 (1.42)	0.02
	VHP+O <sub>3</sub> 5x	3	8.43 (1.50)	0.39	3	10.33 (0.81)	0.29	N/A	N/A	N/A
Breathing Resistance with NaCl Exhalation mmH <sub>2</sub> O ( <i>Standard: ≤25 mm H<sub>2</sub>O for respirators</i> )	Untreated	3	3.30 (0.17)	ref	3	4.13 (0.15)	ref	3	4.70 (0.69)	ref
	MBL 5x	3	3.97 (0.06)	0.003	3	5.33 (0.12)	0.0004	3	3.60 (0.10)	0.11
	DH 5x	3	3.83 (0.25)	0.04	3	4.80 (0.40)	0.054	3	3.50 (0.61)	0.09
	VHP+O <sub>3</sub> 5x	3	4.17 (0.38)	0.02	3	5.60 (0.26)	0.001	N/A	N/A	N/A
Pressure Drop with Bacterial Filtration Efficiency ( <i>Standard: EN 14683:2019 Annex C &lt;40 Pa/cm<sup>2</sup> for Type II and ASTM F2100 spec &lt;6.0 mm H<sub>2</sub>O/cm<sup>2</sup> (158.83 Pa/cm<sup>2</sup> for Type IIR)</i> )	Untreated	10	29.09 (1.76)	ref	10	40.98 (1.03)	ref	10	48.99 (2.17)	ref
	MBL 5x	10	29.09 (1.66)	0.99	10	41.16 (2.19)	0.82	10	51.71 (4.41)	0.10
	DH 5x	10	27.78 (1.69)	0.10	10	40.03 (2.54)	0.29	10	51.22 (3.98)	0.14
	VHP+O <sub>3</sub> 5x	5	32.30 (1.70)	0.005	5	44.48 (3.30)	0.08	N/A	N/A	N/A
Sheffield dummy fit inhalation 28.3 l/m <i>No min requirements for face masks (Modified version EN 149 7.16 was used; Maximum permitted resistance (mbar), inhalation: 0.7 (30 l/min); 2.4 (95 l/min) ) exhalation (160 l/min 3.0)</i>	Untreated	3	-0.18 (0.01)	ref	3	-0.16 (0.02)	ref	3	-0.15 (0.02)	ref
	MBL 5x	3	-0.19 (0.01)	0.26	3	-0.16 (0.01)	0.82	3	-0.15 (0.02)	0.80
	DH 5x	3	-0.17 (0.01)	0.99	3	-0.14 (0.01)	0.48	3	-0.17 (0.02)	0.41
	VHP+O <sub>3</sub> 5x	3	-0.18 (0.02)	0.99	3	-0.15 (0.01)	0.64	N/A	N/A	N/A
Sheffield dummy fit inhalation 85 l/m	Untreated	3	-0.54 (0.06)	ref	3	-0.43 (0.05)	ref	3	-0.49 (0.03)	ref
	MBL 5x	3	-0.61 (0.04)	0.17	3	-0.47 (0.01)	0.31	3	-0.48 (0.03)	0.72
	DH 5x	3	-0.55 (0.02)	0.78	3	-0.46 (0.02)	0.40	3	-0.56 (0.08)	0.20
	VHP+O <sub>3</sub> 5x	3	-0.56 (0.07)	0.72	3	-0.44 (0.03)	0.66	N/A	N/A	N/A

Sheffield dummy fit exhalation 85 l/m	Untreated	3	0.51 (0.05)	ref	3	0.37 (0.04)	ref	3	0.47 (0.03)	ref
	MBL 5x	3	0.55 (0.03)	0.22	3	0.42 (0.01)	0.13	3	0.47 (0.04)	0.92
	DH 5x	3	0.51 (0.01)	0.82	3	0.39 (0.03)	0.51	3	0.53 (0.05)	0.16
	VHP+O <sub>3</sub> 5x	3	0.52 (0.03)	0.63	3	0.40 (0.02)	0.27	N/A	N/A	N/A
Sheffield dummy fit exhalation 160 l/m	Untreated	3	0.97 (0.02)	ref	3	0.71 (0.06)	ref	3	0.92 (0.05)	ref
	MBL 5x	3	1.05 (0.04)	0.37	3	0.81 (0.02)	0.07	3	0.95 (0.09)	0.63
	DH 5x	3	0.97 (0.02)	0.85	3	0.73 (0.03)	0.70	3	1.06 (0.13)	0.16
	VHP+O <sub>3</sub> 5x	3	1.02 (0.08)	0.68	3	0.76 (0.04)	0.33	N/A	N/A	N/A
Fluid Penetration inside surface (% pass) <sup>1</sup> (no Standard)	Untreated	10	60%	ref	10	90%	ref	10	30%	ref
	MBL 5x	10	80%	0.63	10	100%	0.99	10	40%	0.99
	DH 5x	10	50%	0.99	10	90%	0.99	10	50%	0.65
	VHP+O <sub>3</sub> 5x	5	40%	0.61	5	100%	0.99	N/A	N/A	N/A
Fluid Penetration outside surface (% pass) <sup>6</sup> (Standard: ≥90.625% should pass: 29 out of 32 samples according to ASTM F2100)	Untreated	15	33.3%	ref	15	40%	ref	15	93.3%	ref
	MBL 5x	10	50%	0.44	10	40%	0.99	10	60%	0.12
	DH 5x	10	50%	0.44	10	50%	0.70	10	70%	0.27
	VHP+O <sub>3</sub> 5x	5	100%	0.03	5	100%	0.04	N/A	N/A	N/A
Human fit (PortaCount) Overall Fit Factor (No minimum requirements for face masks. Standard for Respirators: Fit factor≥100; OSHA 29 CFR 1910.134(f))	Untreated	5	3.81 (0.82)	ref	5	3.72 (1.00)	ref	5	3.34 (0.78)	ref
	MBL 5x	5	4.11 (0.83)	0.58	5	3.54 (0.67)	0.99	5	2.94 (1.01)	0.40
	DH 5x	5	3.63 (0.87)	74	5	3.65 (1.72)	0.53	5	2.76 (0.67)	0.30
	VHP+O <sub>3</sub> 5x	5	2.41 (0.26)	0.02	5	2.17 (0.39)	0.012	N/A	N/A	N/A
Tensile strength force (Newtons) (no Standard)	Untreated	N/A	N/A	N/A	N/A	N/A	N/A	6	194.35 (3.58)	ref
	MBL 5x	N/A	N/A	N/A	N/A	N/A	N/A	15	170.7 (20.53)	0.006
	DH 5x	N/A	N/A	N/A	N/A	N/A	N/A	15	206.41 (25.62)	0.08
Tensile strength: Elongation (%) (no Standard)	Untreated	N/A	N/A	N/A	N/A	N/A	N/A	6	11.13 (0.21)	ref
	MBL 5x	N/A	N/A	N/A	N/A	N/A	N/A	15	30.35 (5.78)	<0.0001
	DH 5x	N/A	N/A	N/A	N/A	N/A	N/A	15	15.33 (9.87)	0.90
Tensile strength: Maximum load (190% strain) (no Standard)	Untreated	12	0.44 (0.05)	ref	12	0.44 (0.04)	ref	N/A	N/A	N/A
	MBL 5x	25	0.46 (0.03)	0.21	25	0.39 (0.04)	0.001	N/A	N/A	N/A
	DH 5x	21	0.41 90.03)	0.08	21	0.34 (0.05)	0.0001	N/A	N/A	N/A
	VHP+O <sub>3</sub> 5x	10	0.34 (0.03)	<0.0001	10	0.35 (0.03)	<0.0001	N/A	N/A	N/A

\* Difference between results from decontaminated face masks compared to untreated masks (Student's t test, Mann-Whitney U test or Fisher's exact test). Ref = reference category

**Table 2B: Integrity Testing Results for Respirators (FFRs)**

Integrity Test	Decontamination method	Halyard Duck Bill Respirator (RH)			3M half sphere Respirator (RM)			3M 1870+ panel Respirator (R3)		
		N	Mean (SD)	p-value	N	Mean (SD)	p-value	N	Mean (SD)	p-value
NaCl filtration efficiency (%) ( $\geq 95\%$ )	Untreated	4	99.22 (0.17)	ref	4	98.73 (0.65)	ref	2	99.13 (0.41)	ref
	MBL 5x	7	98.98 (0.78)	0.78	7	98.87 (0.24)	0.92	7	99.78 (0.09)	0.057
	DH 5x	7	99.22 (0.28)	0.78	7	98.79 (0.24)	0.78	7	99.39 (0.49)	0.46
	VHP+O <sub>3</sub> 5x	7	98.92 (0.58)	0.78	7	98.47 (0.40)	0.22	7	99.72 (0.15)	0.057
NaCl filter efficiency (%) after loading)	Untreated	3	99.07 (0.33)	ref	3	98.96 (0.27)	ref	5	98.57 (1.75)	ref
	MBL 5x	3	98.72 (0.53)	0.39	3	99.21 (0.13)	0.22	3	98.92 (1.34)	0.99
	DH 5x	3	98.77 (0.50)	0.44	3	98.65 (0.30)	0.25	3	99.23 (0.78)	0.99
	VHP+O <sub>3</sub> 5x	3	99.12 (0.26)	0.82	3	98.75 (0.22)	0.37	3	99.56 (0.16)	0.99
Breathing Resistance with NaCl Inhalation <sup>1</sup> ( $\leq 35$ mmH <sub>2</sub> O)	Untreated	3	8.81 (0.14)	ref	3	7.87 (0.00)	ref	5	5.33 (0.78)	ref
	MBL 5x	3	8.38 (0.00)	0.04	3	7.20 (0.39)	0.06	3	6.86 (0.26)	0.02
	DH 5x	3	8.30 (0.14)	0.012	3	6.69 (0.15)	0.06	3	6.26 (0.39)	0.11
	VHP+O <sub>3</sub> 5x	3	8.21 (0.39)	0.07	3	6.77 (0.15)	0.06	3	6.35 (0.44)	0.09
Breathing Resistance with NaCl Exhalation <sup>2</sup> ( $\leq 25$ mmH <sub>2</sub> O)	Untreated	3	8.89 (0.00)	ref	3	7.79 (0.14)	ref	5	4.88 (0.58)	ref
	MBL 5x	3	8.38 (0.00)	<0.0001	3	7.03 (0.39)	0.03	3	6.10 (0.26)	0.015
	DH 5x	3	8.21 (0.14)	0.015	3	6.77 (0.29)	0.006	3	6.18 (0.39)	0.014
	VHP+O <sub>3</sub> 5x	3	8.72 (0.39)	0.53	3	6.86 (0.00)	0.008	3	5.76 (0.29)	0.053
Sheffield dummy fit inhalation 28.3 l/m (Modified version EN 149 7.16 was used; Maximum permitted resistance (mbar), inhalation: 0.7 (30 l/min); 2.4 (95 l/min) exhalation (160 l/min 3.0)	Untreated	3	-0.27 (0.01)	ref	3	-0.26 (0.02)	ref	3	-0.22 (0.01)	ref
	MBL 5x	3	-0.29 (0.02)	0.20	3	-0.26 (0.01)	0.99	3	-0.23 (0.01)	0.52
	DH 5x	3	-0.26 (0.02)	0.48	3	-0.21 (0.01)	0.007	3	-0.25 (0.01)	0.008
	VHP+O <sub>3</sub> 5x	3	-0.29 (0.02)	0.28	3	-0.25 (0.02)	0.37	3	-0.22 (0.01)	0.23
Sheffield dummy fit inhalation 85 l/m	Untreated	3	-0.85 (0.03)	ref	3	-0.79 (0.05)	ref	3	-0.66 (0.03)	ref
	MBL 5x	3	-0.88 (0.04)	0.36	3	-0.78 (0.04)	0.79	3	-0.68 (0.03)	0.41

	DH 5x	3	-0.80 (0.06)	0.27	3	-0.61 (0.01)	0.004	3	-0.75 (0.03)	0.014
	VHP+O <sub>3</sub> 5x	3	-0.87 (0.04)	0.58	3	-0.74 (0.04)	0.27	3	-0.65 (0.01)	0.57
Sheffield dummy fit exhalation 85 l/m	Untreated	3	0.80 (0.03)	ref	3	0.74 (0.06)	ref	3	0.63 (0.04)	ref
	MBL 5x	3	0.83 (0.03)	0.26	3	0.75 (0.03)	0.93	3	0.66 (0.02)	0.48
	DH 5x	3	0.78 (0.02)	0.30	3	0.59 (0.01)	0.04	3	0.73 (0.01)	0.008
	VHP+O <sub>3</sub> 5x	3	0.84 (0.04)	0.26	3	0.72 (0.03)	0.61	3	0.62 (0.01)	0.88
Sheffield dummy fit exhalation 160 l/m	Untreated	3	1.62 (0.05)	ref	3	1.49 (0.12)	ref	3	1.24 (0.03)	ref
	MBL 5x	3	1.66 (0.01)	0.19	3	1.46 (0.05)	0.99	3	1.28 (0.05)	0.38
	DH 5x	3	1.61 (0.02)	0.92	3	1.15 (0.01)	0.08	3	1.43 (0.03)	0.08
	VHP+O <sub>3</sub> 5x	3	1.69 (0.05)	0.11	3	1.46 (0.02)	0.99	3	1.22 (0.02)	0.38
Human fit (PortaCount) Overall Fit Factor <i>(Standard: Fit factor ≥100; OSHA 29 CFR 1910.134(f))</i>	Untreated	10	150.13 (54.95)	ref	10	149.53 (51.79)	ref	10	175.70 (36.19)	ref
	MBL 5x	10	170.28 (48.76)	0.39	10	142.59 (51.26)	0.56	10	165.51 (50.53)	0.49
	DH 5x	10	173.82 (37.93)	0.31	10	147.23 (46.95)	0.56	9	184.42 (45.00)	0.46
	VHP+O <sub>3</sub> 5x	10	91.67 (82.93)	0.14	10	72.30 (67.33)	0.011	10	159.41 (65.23)	0.77
Manikin (Advanced Headform) Overall Fit Factor <i>(Standard: ≥100 per OSHA 1910.134 (f)(7) through quantitative fit testing)</i>	Untreated	3	188.00 (20.78)	ref	3	200.00 (0.00)	ref	3	195.67 (7.51)	ref
	MBL 5x	2	186.50 (19.09)	0.99	3	188.00 (20.78)	0.51	3	159.33 (13.01)	0.08
	DH 5x	3	163.00 (32.91)	0.35	3	200.00 (0.00)	0.99	3	165.67 (45.08)	0.18
	VHP+O <sub>3</sub> 5x	3	186.00 (24.25)	0.99	3	127.67 (20.78)	0.06	3	195.67 (7.51)	0.99
Tensile strength: Force (Newtons) in top strap ( <i>no Standard</i> )	Untreated	4	2.41 (0.03)	ref	4	2.83 (0.22)	ref	2	1.71 (0.1)	ref
	MBL 5x	5	2.37 (0.02)	0.39	5	2.73 (0.10)	0.71	5	1.77 (0.17)	0.85
	DH 5x	5	2.31 (0.01)	0.02	5	2.71 (0.04)	0.90	5	1.87 (0.03)	0.08
	VHP+O <sub>3</sub> 5x	5	1.99 (0.07)	0.02	5	3.61 (0.30)	0.02	5	1.92 (0.04)	0.08
Tensile strength: Force (Newtons) in bottom strap ( <i>no Standard</i> )	Untreated	4	2.46 (0.04)	ref	4	2.71 (0.20)	ref	2	1.71 (0.15)	ref
	MBL 5x	5	2.42 (0.04)	0.39	5	2.76 (0.10)	0.54	5	1.96 (0.06)	0.02
	DH 5x	5	2.33 (0.03)	0.02	5	2.67 (0.06)	0.99	5	1.73 (0.03)	0.85
	VHP+O <sub>3</sub> 5x	5	2.00 (0.04)	0.02	5	3.62 (0.23)	0.02	5	1.91 (0.08)	0.052

\* Difference between results from decontaminated face masks compared to untreated masks (Student's t test or Mann-Whitney U test). Ref = reference category